

# WEST SYSTEM AND COMPATIBLE PRODUCTS

A general purpose, room temperature cured epoxy.

WEST SYSTEM

WEST SYSTEM AND COMPATIBLE PRODUCTS

CODE: 105      VERSION: 1.1      ISSUE DATE 26/11/2024

## 105 Epoxy Resin

### Introduction

WEST SYSTEM 105 is a low viscosity, solvent free epoxy resin specifically formulated for the use with the WEST SYSTEM range of hardeners to cure at room temperature or low temperature applications in fibre composite boat construction.

It is designed specifically to wet out and bond with wood, fibreglass, reinforcing fabrics and a variety of metals.

As an adhesive, WEST SYSTEM 105 will bridge gaps and fill voids when modified with WEST SYSTEM fillers and can be easily sanded and shaped when cured.

As a coating, WEST SYSTEM 105 has excellent thin-film characteristics to flow out and self-level without "fish eyeing."

### Applications

- Boat construction
- Potting
- Encapsulation
- Sporting equipment
- Coving compound
- Adhesives

### Mix Ratio

See Hardener label.  
Note: Care should be taken to when dispensing and mixing.

Optimum results are achieved when recommended ratios are used.

### Uncured Properties

Physical State	Colourless liquid
Specific Gravity (g/ml)	1.14
Viscosity @ 20°C (cP)	1000

**Note:** Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages.

# WEST SYSTEM AND COMPATIBLE PRODUCTS

A general purpose, room temperature cured epoxy.

WEST SYSTEM

WEST SYSTEM AND COMPATIBLE PRODUCTS


## Cured Properties

	205	206	207	209
Mix Ratio 100 Parts of 105 Resin (by weight)	20	20	29	29
Mix Ratio (by volume)	5 : 1	5 : 1	3 : 1	3 : 1
Pot Life 100g @ 20°C (minutes)	15	22	27	6
Thin Film @ 20°C (minutes)	60 - 70	90 - 110	110 - 130	3 - 4 Hours
Mixed Viscosity @ 20°C	975	725	775	650
HDT after 7 days @ 20°C	52°C	54°C	44°C	65°C
Ultimate HDT	68°C	76°C	60°C	69°C
Typical post cure requirement (6 hours @ 60°C)	24 Hours @ 20°C followed by 6 Hours @ 60°C			

Note: Typical properties and not to be construed as actual specifications, pph = parts per hundred parts of resin

## Cure Development Profiles

The following graphs may be used to predict Cure progression during baking cycles for H206 hardener.



**Note:** Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages.

# WEST SYSTEM AND COMPATIBLE PRODUCTS

A general purpose, room temperature cured epoxy.

**WEST  
SYSTEM**

## Post Cure

Post cures at elevated temperatures will be effective in achieving a fast cure, but longer cure times at a gradually increasing temperature are recommended for achieving ultimate HDT.

## Storage

WEST SYSTEM 105 will keep for 2 years if kept in original containers at room temperature (15°C – 32°C) and out of direct sunlight. Containers should be tightly sealed to prevent moisture absorption.

## Health & Safety

Adhesive Technologies NZ Ltd provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, storage, use and disposal information.

Direct skin contact should be avoided, all amines they have a moderate sensitising potential and should be considered to be mild skin corrosives. WEST SYSTEM 105 system should not be ingested; in an unlikely event WEST SYSTEM 105 is ingested see your nearest physician immediately.

- Use with good ventilation and adequate safety equipment including gloves.
- If skin contact occurs, wash with lanolin based hand-cleaner and water.
- If eye contact occurs, immediately wash for 15 minutes with running water.
- If swallowed:

Resins - DO NOT induce vomiting, and contact a doctor or the Poisons Information Centre.

Hardeners – DO NOT induce vomiting, give plenty of milk or water and contact a doctor or Poisons Information Centre.

**Note:** Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages.